

Gaw House,
Alperton Lane,
Wembley,
Middlesex.
HAO 1WU.
Tel: 020 8998 2171
Fax: 020 8997 9723

WRP Asia Pacific Sdn Bhd.
Lot 1 Jalan 3 Kawasan Perusahaan
Bandar baru Salak Tinggi
43900 Sepang
Selangor Malaysia

EEC COMMISSION DIRECTIVE 90/128/EEC
as amended.

Implemented into UK Law by Statutory Instrument 1998 No 1376.

CERTIFICATE OF CONFORMITY No. CP45763(2)/BW/02

Product Name: Dermagrip Powder Free Latex Exam Glove(cream), Lot # 20502923 .

Sample Received: 30 May 2002.

The product meets the overall migration limit as specified in EEC Commission Directive 90/128/EEC for the foodstuffs listed below in applications up to a temperature of 40°C for a contact time of 2 hours.

Test Conditions:

a) Simulant(s)	Iso Octane	3% w/v acetic acid	10% v/v ethanol
b) Temperature(s)	40°C	40°C	40°C
c) Time(s)	2 hours	2 hours	2 hours

Date of Test: June 2002.

This product is suitable for contact with the following categories of foodstuffs as detailed in EEC Council Directive 85/572/EEC of 19 December 1985.

<u>Description</u>	<u>Ref. from 85/572/EEC</u>	<u>Description</u>	<u>Ref. from 85/572/EEC</u>
Beverages	01.01 01.02 01.03	Animal Products	06.02 06.03 06.04 06.05A 06.06
Bakery Products	02.01 02.02 02 03 02.04 02.05 02.06	Milk Products	06.07 06.08
Confectionery	03.01 03.02A 03.02BII 03.03	Miscellaneous	07.01 07.02 07.03 07.04A 07.04B 07.05
Fruit & Vegetables	04.01 04.02A 04.02B 04.02CI 04.02CIII 04.03A 04.03B 04.04 04.05A 04.05B 04.05CI 04.05CIII		08.01 08.02 08.03A 08.03BII 08.04 08.05 08.06A 08.08 08.09 08.10 08.11 08.12 08.13A 08.14 08.15 08.16 08.17

DATE : 14 June 2002

Certified by:

B Welikala
Analytical Chemist

Approved by:

Paul Foreman
Manager

Member of the SGS Group (Société Générale de Surveillance)



Gaw House
Alperton Lane
Alperton
Wembley
HA0 1WU
Tel: 020 8998 2171
Fax: 020 8997 9723

SGS United Kingdom Ltd
4908 - PPE Suspence account

Attn: Mike Christie

Report No. CP 45763(2)/BW/02

Date : 17 June 2002

Page 1/4

Your Ref. : PP 62711

OVERALL MIGRATION TESTING

SAMPLE DESCRIPTION :The following samples were supplied and sampled by
WRP Asia Pacific Sdn Bhd
Lot 1 Jalan 3 Kawasan Perusahaan
Bandar Baru Salak Tinggi
43900 Sepang
Selangor Malaysia

Dermagrip Powder Free Latex Exam glove (cream), Lot # 20502923.

DATE RECEIVED :30 May 2002.

TEST REQUIRED :Overall Migration Testing.

EXTRACTION CONDITIONS :

1. Iso Octane @ 40°C for 2 hours.
2. 3% w/v Acetic Acid @ 40°C for 2 hours.
3. 10% v/v Ethanol @ 40°C for 2 hours.

DATE OF TEST : June 2002.

Continued ../2

METHOD OF TEST :

Iso Octane, 3% w/v Acetic Acid 10% v/v Ethanol:
Testing was carried out in accordance with SGS In House Procedure No. 7TP011 issue2, which is based on EEC Directive 90/128/EEC and SI3145 (1992).

RESULTS :
See Annexe.

NOTE :

It is the responsibility of the manufacturer to ensure that the concentrations of monomers and additives listed in relevent European Directives and UK Statutory Instruments do not exceed the permitted Limits.

REPORTED BY.....

Bridget Welikala
Analytical Chemist

AUTHORISED BY.....

Paul Foreman
Manager

Continued ../3

ANNEXE

The samples were tested using single side Immersion Extraction and in the test a 1dm^2 of sample was assumed a 1dm^2 surface area.

The results of the migration tests in this report are not divided by the 'reduction factor' referred to in the EEC Directive 85/572/EEC.

Iso Octane :	<u>Sample</u>	<u>Migration mg/dm²</u>
	A	35.1
	B	35.9 35.2 mg/dm ²
	C	34.5 mean

COMMENTS

The EEC Directive 90/128/EEC as amended by Directives 92/39/EEC and 93/9/EEC, is implemented into UK Law by Statutory Instrument No.3145 (1992) which is amended by SI 1995/360, The Plastic Materials and Articles in contact with Food (Amendment) Regulations 1995.

The Overall Migration Limit as stated in the Directive and Statutory Instrument is 10mg/dm^2 .

With regard to the simulant D substitute, this is a more aggressive extractant than most of the foodstuffs it simulates and in most cases the migration result is divided by a reduction factor (specified for each class of foodstuff in Directive 85/572/EEC and ranging from 2-5) before comparison with the 10mg/dm^2 limit. Consequently the sample complies with the Directive for those foodstuffs with a reduction factor of 4 and above as detailed in the Certificate of Conformity.

Continued ../4

10% v/v Ethanol :	<u>Sample</u>	<u>Migration mg/dm²</u>
	A	1.2
	B	1.3 1.2 mg/dm ²
	C	1.2 mean

3% w/v Acetic Acid :	<u>Sample</u>	<u>Migration mg/dm²</u>
	A	1.1
	B	1.5 1.3 mg/dm ²
	C	1.3 mean

COMMENTS

The EEC Directive 90/128/EEC as amended by Directives 92/39/EEC and 93/9/EEC, is implemented into UK Law by Statutory Instrument No.3145 (1992) which is amended by SI 1995/360, The Plastic Materials and Articles in contact with Food (Amendment) Regulations 1995.

The Overall Migration Limit as stated in the Directive and Statutory Instrument is 10 mg/dm². Therefore the samples tested in this report are in compliance with the regulations when tested as described.